KB12150EV 12V 150Ah C_3

The Electric Vehicle batteries were developed based on a specialized grid as well as active material. These batteries have anchored plates and a high impact reinforced polypropylene case which can withstand the most extreme environments and vibrations. The KB EV series is constituted of batteries of several different sizes so that they may be used for many different applications. The KB EV series uses dry cell technology that allows for a superior performance and an unparalleled quality and reliability. Through the use of the dry cell technology this series was designed for sensitive environments that require improved life cycles for commercial, industrial, residential and private applications. Without any need for maintenance and with an advanced construction the EV series is an excellent option for many applications.

Dimensions and Terminal (Unit: mm (inches))



Performance Characteristics

Nominal Voltage	12V	
Dimensions	Length (mm / inch)	481 / 18.9
	Width (mm / inch)	170 / 6.69
	Height (mm / inch)	239 / 9.41
	Total Height (mm / inch)	239 / 9.41
Approx. Weight	(Kg / lbs)	50.0 / 110.2
Design Life	5 years	
Terminal	M8	
Container Material	ABS	
Rated Capacity	170 Ah / 17.0 A	(10hr, 1.75V / cell, 20ºC / 77ºF)
	150 Ah /50.0 A	(3hr, 1.75V / cell, 20ºC / 77ºF)
	126 Ah / 126 A	(1hr, 1.75V / cell, 20ºC / 77ºF)
Operating Temp. Range	Discharge : -20 ~ 50ºC (-4 ~ 122ºF)	
	Charge : -20 ~ 50ºC (-4 ~ 122ºF)	
	Storage : -20 ~ 50ºC (-4 ~ 122ºF)	
Charge Method	Float use: 13.7~13.9V at 25ºC (77ºF)	
	Cycle use: 14.7~14.9V at 25ºC (77ºF)	
	Max charge current 22.5A	
Self Discharge	Fully charged Kaise Electric Vehicle batteries may be stored for up to 6 months at 25ºC (77ºF) and then a freshening charge is required. For higher temperatures the time interval will be shorter.	

Applications

Electric wheelchair
Electric vehicle / golf car
Electric toys
Renewable energies
Marine equipment

Certifications

ISO 9001 / ISO 14001

Discharge Current vs. Discharge Voltage

Final discharge voltage V/CELL	1,8	1,75	1,7	1,6
Discharge current (A)	I ≤ 0,1CA	0.25CA ≥ I > 0.1CA	0.55CA ≥ I > 0.25CA	I > 0.55CA

Constant Current Discharge (Amperes) at 25ºC (77ºF)

Volts/cell	30min	1h	2h	3h	5h	8h	10h	20h
1.80V	207	123	68.8	49.8	31.2	20.2	16.8	9.26
1.75V	216	126	70.0	50.0	32.0	20.2	17.0	9.30
1.70V	218	128	71.0	50.6	32.4	20.4	17.2	9.34
1.65V	222	129	71.7	51.4	32.8	20.6	17.3	9.40
1.60V	226	130	72.1	51.9	33.0	20.8	17.5	9.43

Constant Power Discharge (Watts per cell) at 25ºC (77ºF)

Volts/cell	30min	1h	2h	3h	5h	8h	10h	20h
1.80V	392	237	134	96.1	60.7	39.3	32.4	18.3
1.75V	403	240	134	96.3	61.5	39.6	32.7	18.4
1.70V	405	242	135	96.9	61.9	39.8	32.9	18.5
1.65V	405	244	136	97.5	62.2	40.0	33.3	18.6
1.60V	409	246	136	98.8	62.5	40.4	33.7	18.7

(Note) The above characteristics data are average values obtained within three charge/discharge cycles not the mimimum values.

KB12150EV 12V 150Ah C_3

Disharging Characteristic



Charging Characteristics



The effect of discharge depth on cycle life



Temperature Effects on Capacity



IMPORTANT NOTE: The specifications presented herein are subject to revision without notice.

2025/V/K

Contacto
customer.energy@tempelgroup.com
www.tempelgroup.com

Tempel Group en el mundo
HOUSTON · BARCELONA · MADRID · VALENCIA · BILBAO · SEVILLA · LISBOA · PORTO · ROMA · BUENOS AIRES · LIMA
SANTIAGO DE CHILE · BOGOTÁ · SÃO PAULO · CIUDAD DE MÉXICO · MONTERREY · CIUDAD DE PANAMÁ · MONTEVIDEO · QUITO